

509, 854

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau

31 SEP 2004

(43) International Publication Date  
9 October 2003 (09.10.2003)

PCT

(10) International Publication Number  
**WO 03/082743 A1**

- (51) International Patent Classification<sup>7</sup>: C01G 23/053, B01J 21/06 (74) Agent: BERGGREN OY AB; P.O. Box 16, FIN-00101 Helsinki (FI).
- (21) International Application Number: PCT/FI03/00251 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 1 April 2003 (01.04.2003)
- (25) Filing Language: Finnish
- (26) Publication Language: English
- (30) Priority Data: 20020624 2 April 2002 (02.04.2002) FI (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): KEMIRA PIGMENTS OY [FI/FI]; Porkkalankatu 3, FIN-00180 Helsinki (FI).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): KARVINEN, Salla [FI/FI]; Kuusamantie 37, FIN-28660 Pori (FI). LAMMIN-MÄKI, Ralf-Johan [FI/FI]; Pajatie 5, FIN-28450 Ulvila (FI).
- Published:**  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: A PHOTOCATALYST CONTAINING TITANIUM OXIDE, THE PRODUCTION METHOD AND USE OF THE SAME

(57) Abstract: The invention relates to a photocatalyst containing titanium dioxide, to a method for using it and to its application. A sulphurous titanium dioxide hydrate precipitate is precipitated from an acid titanium oxysulphate solution at a temperature below the boiling point of the solution, e.g. in the range from 70 to 100°C, using crystal nuclei and without addition of base. The precipitate is separated, washed and calcinated. The photocatalytic titanium dioxide thus obtained has a specific area in the range from 100 to 250 m<sup>2</sup>/g and a 0.3 to 5% sulphur concentration. Catalytic activity has been confirmed in asetal dehyde decomposition and in anionic (SNC<sup>-</sup>)<sub>2</sub> radical formation.



WO 03/082743 A1